




Technical Specifications

Lapboard 13x102

Plantation Timber | Sustainable | Ethically Sourced | Carbon Efficient | Environmentally Friendly | Long Lasting



Section Detail



Species	Pinus Radiata
Country of Origin	South Africa
Dimensions	13mm x 102mm
Available Lengths	1200mm to 3000mm (300mm intervals) 3000mm to 4800mm (600mm intervals)
Density	730kg/m ³
Avg Weight	1.06kg/m
Structural Class	N/A
Avg Moisture Content Before Drying	25%
Modulus of Elasticity	7800 N/mm ²
Type or Method of Treatment	Kiln Dried and Pressure Treated
Treatment	CCA or TAN-E or VACSOL
Total Radial Shrinkage	4.20%
Total Tangential Shrinkage	9.50%